# TECHNICAL DATA SHEET



# SHOWA DENKO K.K.

13-9, Shiba Daimon 1-chome Minato-ku, TOKYO, 105-8518, Japan

TEL: +81-3-5403-5600 FAX: +81-3-5403-5720

# Bisphenol A type Vinyl ester resin

# Ripoxy™ R-804JB

# Characteristics

- ·Excellent Chemical Resistance, especially against Acids, Alkalis and solvents
- ·High mechanical strength for FRP
- ·Excellent fatigue strength and excellent toughness

## Advantages

·Lower viscosity : can use smoothly

· Quick curing

·In cobalt type: no need cobalt

Longer shelf lifeLess Bubble

## **Applications**

- ·Chemical tanks, pipes, scrubbers, ducts
- ·Floor lining, Waterproof lining,
- ·Waste treatment systems lining
- ·Marine (yachts and boats)
- · High strength FRP

## 1. Properties of liquid resin

Property	Unit	Value
Appearance	-	Clear red
Viscosity	dPa·s/25°C	2.0 - 3.5
Gel time	Min	20.0 - 30.0
Shelf life	Months/25°C	5

<sup>\*</sup>Gel time: 25 °C 55% MEKPO 1.5phr

# 2. Properties of cured resin

roperties of cured resin							
Property	Unit	Cast	Laminate	Test method			
Flexural strength	MPa	144	184	ASTM D790			
Flexural modulus	GPa	3.6	7.6	ASTM D790			
Tensile strength	MPa	82	111	ASTM D638			
Tensile elongation	%	5.4	2.0	ASTM D638			
Heat distortion temperature	°C	107	-	ASTM D648			
Barcol Hardness	-	41	50	ASTM D2583			
Curing shrinkage	%	7.6	-	ASTM D2566			

<sup>\*</sup>Laminated constitution: 3mats (450g/m²), glass contents 30%

# 3. Curing properties (Gel time)

Temperature (°C)	Materials	15-25min	25-35min	35-60min
20	MEKPO (%)	<del>_</del>	1.5	1.2
	DMA (%)	_	0.06	0.06
25	MEKPO (%)	2.1	1.7	1.5
30	MEKPO (%)	1.7	1.5	1.2
35	MEKPO (%)	1.5	1.3	1.1

\*MEKPO: Butanox M-50 : Akzo novel

\*DMA : Dimethylaniline

#### Precautions for Handling

#### 1. <u>Industrial safety and health precautions</u>

- ·Styrene contained, if inhaled, it could cause organic solvent poisoning and other health damages.
- ·When using Ripoxy, secure proper mechanical ventilation and wear anti-organic gas mask or air-supplied respirator and proper protective clothes to prevent any contact with the body.

# 2. Storage and handling precautions

- ·Ripoxy is a flammable liquid in Class 3 under the United Nation Law
- ·Handling should be made away from heat or fire, and storage must conform

#### 3. Precautions in use

• When using Curing agent and Promoter, stir the Promoter well first and then add the Curing agent (Simultaneous addition must be made because it would cause explosive decomposition)

## 4. First aid

·When Ripoxy gets into the eyes, wash away with abundant water for at least 15 minutes, and see the doctor if there is pain or change in appearance.

#### 5. <u>Disposal precautions</u>

- •Dispose after the content is completely used up.
- Any surplus resin containing curing agent and/or promoter must be cured in a water bath. (If disposed before curing, the curing exothermicity could trigger spontaneous combustion.)

# 6. Other precautions

•For detailed information on the safe handling of Ripoxy , please make sure to read before using the separately prepared 'Safety Data Sheet'.

The information presented herein, while not guaranteed, is true and accurate to the best of our knowledge.

However, no warranty or guarantee is made regarding the performance or stability of any product since the manner of use and condition of storage and handling are beyond our control.